InLube® PEIGF10TF15HFMD

Product Description 10% GLASS FIBER REINFORCED, 15% PTFE LUBRICATED, HIGH FLOW POLYETHERIMIDE

Material Status Commercial: Active

Availability Africa & Middle East, Asia Pacific, Europe, Latin America, North America

Filler / Reinforcement Glass Fiber, 10% Filler by Weight

Additive PTFE Lubricant: 15%

Features Autoclave Sterilizable, Chemical Resistant, E-beam Sterilizable, Ethylene Oxide Sterilizable, Filled, Good Dimensional Stability, Good Mold Release, Heat Sterilizable, High Flow, High Stiffness, High Strength, Low Friction, Lubricated, Radiation Sterilizable, Steam Sterilizable, Wear Resistant

Uses Connectors, Electrical/Electronic Applications, Engineering Parts, Industrial Parts, Medical/Healthcare Applications, Metal Replacement, Semiconductor Applications, Surgical Instruments

Forms Pellets

Processing Method Injection Molding

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.43	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Water Absorption (24 hr)	0.21	%	ASTM D570

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	97.9	MPa	ASTM D638
Tensile Elongation (Yield)	3.0 to 5.0	%	ASTM D638
Flexural Modulus	5170	MPa	ASTM D790
Flexural Strength	165	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	48	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	320 to 430	J/m	ASTM D4812

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	207	°C	

Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.6 mm)	V-0		UL 94

Properties provided are only typical values and Americhem assumes no liability for the customer's use of the information provided. The customer assumes all responsibility for testing determining this products suitability in the customer's specific end application.

Revision Date: 1/13/2025

Americhem World Headquarters
2000 Americhem Way
Cuyahoga Falls, OH 44221
Tel: +1 330 929 4213
Toll Free: +1 800 228 3476

Americhem Engineered Compounds
20 Progress Drive
Morrisvillle, PA 19067
Tel: +1 215 736 1126
Toll Free: +1 800 863 4260

InLube® PEIGF10TF15HFMD

Polyetherimide

Injection	Nominal Value	Unit
Drying Temperature	149	°C
Drying Time	3.0 to 4.0	hr
Processing (Melt) Temp	354 to 385	°C
Mold Temperature	149 to 177	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm
Vent Depth	0.038 to 0.076	mm

Notes

[1] Typical properties: these are not to be construed as specifications.

Properties provided are only typical values and Americhem assumes no liability for the customer's use of the information provided. The customer assumes all responsibility for testing determining this products suitability in the customer's specific end application.

Revision Date: 1/13/2025

Americhem World Headquarters
2000 Americhem Way
Cuyahoga Falls, OH 44221
Tel: +1 330 929 4213
Toll Free: +1 800 228 3476

Americhem Engineered Compounds
20 Progress Drive
Morrisvillle, PA 19067
Tel: +1 215 736 1126
Toll Free: +1 800 863 4260