KYNAR FLEX®

TECHNICAL DATA SHEET

KYNAR FLEX® 3120-50

FLUORINATED COPOLYMER PELLET

KYNAR FLEX® resins are fluorinated thermoplastic copolymers.
KYNAR FLEX® 3120-15 resin has been specifically designed for use in wire and cable constructions which require a 150ºC rating and improve flame and smoke resistance.
KYNAR FLEX® 3120-15 resin is easily processed and has excellent physical, mechanical, thermal and flame resistant characteristics. Its low viscosity allows easy processing.

Additional Characteristics:
- Excellent thermal stability
- Excellent abrasion resistance
- High Limiting Oxygen Index
- Extremely low smoke emission characteristics

TYPE

PVDF

MAIN APPLICATIONS

- plenum conduit
- plenum cable

DELIVERY FORM

- Pellets

ADDITIVES

- Lubricants

RHEOLOGICAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Melt viscosity, 230°C (446°F) at 100 s-1	20 - 26	kPo	ASTM D3835
Melt flow index (MFR), 230°C / 5 kg (446°F / 11 lb)	2.5 - 7.5	g/10min	ASTM D1238
Melt volume flow rate (MVR), 230°C / 12.5 kg (446°F / 27.5 lb)	0.5	cm^3/10min	ISO 1133

MECHANICAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Yield stress, 23°C (73°F)	24.1 - 34.5	MPa	ASTM D638
Yield strain, 23°C (73°F)	15	%	ISO 527-1/-2
Stress at break, 23°C (73°F)	34.5 - 48.3	MPa	ASTM D638
Nominal strain at break, 23°C (73°F)	>50	%	ISO 527-1/-2
Compression strength, 23°C (73°F)	31 - 41.4	MPa	ASTM D695
Izod impact unnotched strength, 23°C (73°F)	No Break		ASTM D256
Izod impact notched strength, 23°C (73°F)	No Break		ASTM D256
Charpy notched impact strength, 23°C (73°F)	No Break		ISO 179 1eA
Hardness, shore D	65 - 70		ASTM D2240
Flexural modulus, 23°C (73°F)	621 - 827	MPa	ASTM D790
Tensile modulus, 23°C (73°F)	700	MPa	ASTM D638
Coefficient of friction dynamic vs steel, 23°C (73°F)	0.3		ASTM D1895

KYNAR FLEX® 3120-50

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Coefficient of friction static vs steel, 23°C (73°F)	0.31		ASTM D1894
Abrasion resistance, wheel CS 17, load 1 kg, 1000 cycles	16 - 19	mg	ASTM G195-13A

THERMAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Glass transition temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Limiting oxygen index (LOI)	42	%	ASTM D2863
Yellow card available	yes		
Coefficient of linear thermal expansion, 23°C (73°F)	126 - 185	10E-6 / °K	ASTM D696
Specific heat temperature, 23°C (73°F)	745 - 958		ISO 11357-1/-2
Heat deflection temperature, 1.8 MPa	50	°C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa, 138°C/h	43.3 - 54.4	°C	ASTM D648
Heat deflection temperature, 0.45 MPa, 138°C/h	54.4-76.7	°C	ASTM D648
Thermal conductivity	0.144 - 0.18	W/m-K	ASTM D433
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3

ELECTRICAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Dielectric constant, 1kHz	3.2 - 10.2		ASTM D150
Surface resistivity, 23°C (73,4°F)	5.3E+11 - 5.5E+11	ohm/sq	ASTM D257
Dielectric strength, 23°C (73,4°F)	1.3 - 1.5	kV/mm	ASTM D149
Relative thermal index	150		
Dissipation factor	0.02 - 0.19		ASTM D150

OTHER PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Density, 23°C (73°F)	1.75 - 1.77	g/cm³	ISO 1183-1
Water absorption, at equilibrium at 23°C (73°F) / Immersion	0.03	%	ISO 62

PACKAGING

Available packaging:
- 1000 kg / 2205 lb rigid container
- 25 kg / 55 lb rigid container
- 500 kg big bag
- 680 kg / 1500 lb big bag
- 680 kg /1500 lb rigid container
- 750 kg / 1650 lb rigid containers

SPECIAL CHARACTERISTICS

- Flame & smoke

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790
arkema.com