Monprene® OM-12250-02

Teknor Apex Company - Thermoplastic Elastomer

Wednesday, April 1, 2026

General Information

Product Description

Monprene OM-12250-02 is a specialty thermoplastic elastomer designed for overmolding and co-extrusion applications like grips and anti-skid parts for consumer and industrial products. Monprene OM-12250-02 is a medium hardness, medium density, RoHS compliant grade that exhibits excellent adhesion to PC, ABS, and PC/ABS.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Good Colorability • Good Compression Set • Good Mold Release	• Good Moldability • Good Processability • Light Stabilized • Low Flow	• Lubricated • Medium Density • Medium Hardness • Without Fillers
Uses	• Appliances • Bonding • Cell Phones • Flexible Grips	• Handles • Knobs • Overmolding • Power/Other Tools	• Sporting Goods • Writing Instruments
Agency Ratings	• UL 94		
RoHS Compliance	• RoHS Compliant		
UL File Number	• QMFZ2.E54709		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.980		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress [2]			ASTM D412
Across Flow : 100% Strain	242	psi	
Flow : 100% Strain	296	psi	
Tensile Stress [2]			ASTM D412
Across Flow : 300% Strain	418	psi	
Flow : 300% Strain	479	psi	
Tensile Strength [2]			ASTM D412
Across Flow : Break	1120	psi	
Flow : Break	1100	psi	
Tensile Elongation [2]			ASTM D412
Across Flow : Break	670	%	
Flow : Break	670	%	
Tear Strength [2]			ASTM D624
Across Flow	172	lbf/in	
Flow	162	lbf/in	
Compression Set [3]			ASTM D395B
73°F, 22 hr	18	%	
158°F	65	%	

Revision Date: 6/18/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Monprene® OM-12250-02

Teknor Apex Company - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	52		
Shore A, 1 sec, Injection Molded [4]	62		
Shore A, 5 sec, Injection Molded [4]	60		

Thermal	Nominal Value	Unit	Test Method
RTI Elec	122	°F	UL 746B
RTI Imp	122	°F	UL 746B
RTI Str	122	°F	UL 746B

Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in, All Colors)	HB		UL 94

Additional Information	Nominal Value	Unit
Adhesion to ABS		
Adhesion to PC		
Adhesion to PC/ABS		

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	140	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	320 to 380	°F
Middle Temperature	320 to 380	°F
Front Temperature	320 to 380	°F
Nozzle Temperature	320 to 380	°F
Processing (Melt) Temp	320 to 380	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Back Pressure	25.0 to 125	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Moisture can degrade the material. Drying is suggested. This can be accomplished by placing the material in a desiccant dryer for 2 to 4 hours at 140°F (60°C).

For any overmolding process it is recommended that the process temperatures for the TPE material be set at least 50°F (10°C)higher than the melt temperature of the substrate material.

Revision Date: 6/18/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Monprene® OM-12250-02

Teknor Apex Company - Thermoplastic Elastomer

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	320 to 360	°F
Cylinder Zone 2 Temp.	320 to 360	°F
Cylinder Zone 3 Temp.	320 to 360	°F
Cylinder Zone 4 Temp.	320 to 360	°F
Cylinder Zone 5 Temp.	320 to 360	°F
Die Temperature	320 to 360	°F

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] Die C, 20 in/min

[3] Type 1

[4] Aged for 48 hr

Teknor Apex Company
Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan 22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknoapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 6/18/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector