KYNAR FLEX®

TECHNICAL DATA SHEET

KYNAR FLEX® 2850-07

FLUORINATED COPOLYMER PELLET

KYNAR FLEX® resins are fluorinated thermoplastic copolymers.
Outstanding characteristics: chemical resistance, resistance to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties.
KYNAR FLEX® 2850-07 resin is a moderate viscosity version of KYNAR FLEX® 2850-00 resin in for ease of extrusion and co-extrusion.
It has a UL RTI temperature rating of 140 degrees C.

TYPE

PVDF

MAIN APPLICATIONS

- molding
- tubing

DELIVERY FORM

- Pellets

RHEOLOGICAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Melt viscosity, 230°C (446°F) at 100 s-1	16 - 20	kPo	ASTM D3835
Melt flow index (MFR), 230°C / 5 kg (446°F / 11 lb)	9 - 16	g/10min	ASTM D1238

MECHANICAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Yield stress, 23°C (73°F)	31 - 41.4	MPa	ASTM D638
Yield strain, 23°C (73°F)	11	%	ISO 527-1/-2
Stress at break, 23°C (73°F)	27.6 - 48.3	MPa	ASTM D638
Nominal strain at break, 23°C (73°F)	>50	%	ISO 527-1/-2
Compression strength, 23°C (73°F)	41.4 - 58.6	MPa	ASTM D695
Izod impact unnotched strength, 23°C (73°F)	No Break		ASTM D256
Izod impact notched strength, 23°C (73°F)	0.16 - 0.427	J/m	ASTM D256
Charpy notched impact strength, 23°C (73°F)	No Break		ISO 179 1eA
Hardness, shore D	70 - 75		ASTM D2240
Flexural modulus, 23°C (73°F)	1030 - 1240	MPa	ASTM D790
Tensile modulus, 23°C (73°F)	1300	MPa	ASTM D638
Coefficient of friction dynamic vs steel, 23°C (73°F)	0.19		ASTM D1895
Coefficient of friction static vs steel, 23°C (73°F)	0.26		ASTM D1894
Abrasion resistance, wheel CS 17, load 1 kg, 1000 cycles	6 - 9	mg	ASTM G195-13A

KYNAR FLEX® 2850-07

THERMAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Limiting oxygen index (LOI)	43	%	ASTM D2863
Yellow card available	yes		
Coefficient of linear thermal expansion, 23°C (73°F)	126 - 185	10E-6 / °K	ASTM D696
Specific heat temperature, 23°C (73°F)	745 - 958		ISO 11357-1/-2
Heat deflection temperature, 1.8 MPa, 138°C/h	37.8 - 55	°C	ASTM D648
Heat deflection temperature, 0.45 MPa, 138°C/h	60-75	°C	ASTM D648
Glass transition temperature	-40.6 - -38.3	°C	ASTM D7028
Thermal conductivity	0.144 - 0.18	W/m-K	ASTM D433
Melting temperature, 10°C/min	157	°C	ISO 11357-1/-3
Burning behavior, nominal thickness 1.5 mm	V-0		IEC 60695-11-10

ELECTRICAL PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Dielectric constant, 1kHz	3.5 - 10.2		ASTM D150
Relative permittivity, 100Hz	6.85		IEC 62631-2-1
Relative thermal index	140		
Dissipation factor, 100Hz	0.12	E-4	IEC 62631-2-1
Dissipation factor	0.01 - 0.22		ASTM D150

OTHER PROPERTIES

PROPERTIES	TYPICAL VALUE	UNIT	TEST STANDARD
Density, 23°C (73°F)	1.77 - 1.8	g/cm³	ISO 1183-1
Water absorption, at equilibrium at 23°C (73°F) / Immersion	0.03	%	ISO 62

PACKAGING

Available packaging:
- 1000 kg / 2205 lb rigid container
- 25 kg / 55 lb rigid container
- 680 kg / 1500 lb big bag
- 680 kg /1500 lb rigid container

SPECIAL CHARACTERISTICS

- Flame & smoke

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790
arkema.com