ENSOFT SL-154-50A

Ravago Manufacturing Turkey - Thermoplastic Elastomer

Friday, March 6, 2026

General Information

Product Description

This polyolefin based thermoplastic elastomer (SEBS) compound is high mineral filled, completely recyclable and possible alternative to replace PVC in various applications. ENSOFT® series can be processed with conventional thermoplastics machinery

Additive Packages :
T / Heat and UV stabilizer

Key Features :
Good ozone and UV resistance
Easy processing
Rubberlike elasticity
Easy colorability with proper MB (PE, PP, etc. based)

Process Method :
Extrusion, coextrusion, sheet extrusion

Uses :
Extruded parts (seals, tubes, profiles, hoses, etc.) for construction and furniture

General			
Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Filler / Reinforcement	• Mineral		
Additive	• Heat Stabilizer	• UV Stabilizer	
Features	• Chemical Resistant • Good Colorability • Good Processability	• Heat Stabilized • High Elasticity • Ozone Resistant	• Recyclable Material • UV Resistant • UV Stabilized
Uses	• Construction Applications • Furniture	• Hose • Profiles	• Seals • Tubing
Processing Method	• Coextrusion	• Extrusion	• Sheet Extrusion

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm³	ISO 1183/A
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress (100% Strain)	1.20	MPa	ISO 37
Tensile Stress (300% Strain)	1.80	MPa	ISO 37
Tensile Stress (Break)	3.60	MPa	ISO 37
Tensile Elongation (Break)	690	%	ISO 37
Tear Strength - Across Flow	19.0	kN/m	ISO 34-1
Compression Set (23°C, 72 hr)	23	%	ASTM D395B
Hardness	**Nominal Value**	**Unit**	**Test Method**
Shore Hardness (Shore A, 3 sec)	50		ISO 868

the data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. no liability, warranty or guarantee of product performance is created by this document. ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

ENSOFT SL-154-50A

Ravago Manufacturing Turkey - Thermoplastic Elastomer

Thermal	Nominal Value	Unit
Brittleness Temperature	-55.0	°C
Service Temperature		
Dynamic	90	°C
Static	110	°C

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	170 to 190	°C
Cylinder Zone 3 Temp.	180 to 195	°C
Cylinder Zone 5 Temp.	195 to 205	°C
Adapter Temperature	200 to 210	°C
Die Temperature	200 to 220	°C

Notes

[1] Typical properties: these are not to be construed as specifications.

the data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. no liability, warranty or guarantee of product performance is created by this document. ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.