Sarlink® TPE ME-2680 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Friday, April 3, 2026

General Information

Product Description

The Sarlink ME-2600 Series is a super high flow high performance thermoplastic elastomer series, available in BLK, designed for automotive exterior molded applications, including window encapsulation. Sarlink ME-2680B is a high hardness, low density, resilient, UV stabilized, super high flow injection molding grade delivering excellent aesthetics with good adhesion to glass with primer.

General			
Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Ablation Resistant • Abrasion Resistant • Anti-fogging • Bondability • Chemical Resistant • Filled • General Purpose • Good Adhesion • Good Color Stability • Good Colorability	• Good Flexibility • Good Moldability • Good Processability • Good Scratch Resistance • Good Tear Strength • Halogen Free • High Elasticity • High Flow • High Hardness • High Tensile Strength	• Low Compression Set • Low Density • Low Gloss • Lubricated • Paintable • Pleasing Surface Appearance • UV Resistant • Wear Resistant
Uses	• Automotive Applications • Automotive Exterior Parts • Automotive Exterior Trim	• Automotive Interior Parts • Automotive Interior Trim • Automotive Window Encapsulation	• Overmolding • Rubber Replacement
RoHS Compliance	• RoHS Compliant		
Appearance	• Black • Colors Available	• Natural Color • Opaque	
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density	0.940	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	23	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress [2]			ISO 37
Across Flow : 100% Strain	497	psi	
Flow : 100% Strain	624	psi	
Tensile Stress [2]			ISO 37
Across Flow : Break	1610	psi	
Flow : Break	1460	psi	
Tensile Elongation [2]			ISO 37
Across Flow : Break	760	%	
Flow : Break	640	%	
Tear Strength [3]			ISO 34-1
Across Flow	213	lbf/in	
Flow	192	lbf/in	

Revision Date: 10/11/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Sarlink® TPE ME-2680 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Elastomers	Nominal Value	Unit	Test Method
Compression Set [4]			ISO 815
73°F, 72 hr	35	%	
158°F, 22 hr	59	%	
212°F, 22 hr	67	%	
257°F, 70 hr	88	%	
Hardness	**Nominal Value**	**Unit**	**Test Method**
Shore Hardness			ISO 868
Shore A, 1 sec, Injection Molded	84		
Shore A, 5 sec, Injection Molded	83		
Shore A, 15 sec, Injection Molded	82		
Aging	**Nominal Value**	**Unit**	**Test Method**
Change in Tensile Strength in Air			ISO 188
Across Flow : 230°F, 1008 hr [5]	5.1	%	
Flow : 230°F, 1008 hr [5]	4.3	%	
Across Flow : 257°F, 1008 hr [6]	-9.0	%	
Flow : 257°F, 1008 hr [6]	2.0	%	
Change in Tensile Strain at Break in Air			ISO 188
Across Flow : 230°F, 1008 hr [5]	13	%	
Flow : 230°F, 1008 hr [5]	13	%	
Across Flow : 257°F, 1008 hr [6]	3.8	%	
Flow : 257°F, 1008 hr [6]	15	%	
Change in Shore Hardness in Air [7]			ISO 188
Shore A, 230°F, 1008 hr	1.1		
Shore A, 257°F, 1008 hr	1.0		
Fill Analysis	**Nominal Value**	**Unit**	**Test Method**
Apparent Viscosity (392°F, 206 sec^-1)	175	Pa·s	ASTM D3835

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	380 to 480	°F
Middle Temperature	380 to 480	°F
Front Temperature	380 to 480	°F
Nozzle Temperature	380 to 480	°F
Processing (Melt) Temp	380 to 480	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Fast	
Back Pressure	25.0 to 125	psi
Screw Speed	50 to 120	rpm
Cushion	0.150 to 1.00	in

Revision Date: 10/11/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector

Sarlink® TPE ME-2680 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] Type 1, 20 in/min

[3] Method Ba, Angle (Unnicked), 20 in/min

[4] Type A

[5] Type 1

[6] Type 2

[7] 15 sec delay

Teknor Apex Company
Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan 22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknoapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 10/11/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2026 UL Prospector