Versaflex™ CE 3120-80 TYF Black HT

Thermoplastic Elastomer

Key Characteristics

Product Description			
Versaflex CE 3120-80 TYF Black HT is a customized grade designed for overmolding onto polycarbonate (PC), ABS,PC/ABS substrates.			
General			
Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific		
Features	• Soft	• UV Stabilized	
Uses	• Consumer Applications	• Electrical/Electronic Applications	• Overmolding
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.05	1.05	ASTM D792
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Stress [2, 3] (300% Strain, 73°F (23°C))	897 psi	6.18 MPa	ASTM D412
Tensile Strength [2, 3] (Break, 73°F (23°C))	2760 psi	19.0 MPa	ASTM D412
Tensile Elongation [2, 3] (Break, 73°F (23°C))	500 %	500 %	ASTM D412
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Durometer Hardness			ASTM D2240
Shore A, 10 sec, 73°F (23°C)	79	79	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	< 0.040 %	< 0.040 %
Rear Temperature	338 to 356 °F	170 to 180 °C
Middle Temperature	347 to 392 °F	175 to 200 °C
Front Temperature	365 to 410 °F	185 to 210 °C
Nozzle Temperature	374 to 428 °F	190 to 220 °C
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	50 to 122 °F	10 to 50 °C
Back Pressure	14.5 to 218 psi	0.100 to 1.50 MPa
Screw Speed	50 to 80 rpm	50 to 80 rpm

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection Notes
Versaflex CE 3120-80 TYF Black HT must be dried in the dehumidification dryer and the dewpoint must be set at -40°C or below. The molecular sieve of dehumidification dryer should be active. This material should not be left in the barrel for extended idle periods (greater than 5 minutes). Hot Runners :190 to 226°C Hot tip:190 to 232°C Injection speed: low to middle, suggested: 12 to 45 mm/s 1st stage -Boost Pressure: 500 to 1200 psi 2nd stage- Hold pressure: 20 to 60% of Boost Hold time (Thick Part): 2 to 4 sec Hold time (Thin Part) 1 to 2 sec The injection parameters here mentioned is typical value based on our experience, the user are suggested to pay attention and optimize the parameters according to the exact application.

Notes

[1] Typical values are not to be construed as specifications.

[2] Die C

[3] 2 hr

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.