GLS AD4-849B

Thermoplastic Elastomer

Key Characteristics

Product Description		
GLS AD4-849B is a customized material for injection molding applications.		
General		
Material Status	• Commercial: Active	
Regional Availability	• Asia Pacific	
Features	• Abrasion Resistant	• High Strength
Appearance	• Blue	
Forms	• Pellets	
Processing Method	• Extrusion	• Injection Molding

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.21	1.21	ASTM D792
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Stress (300% Strain)	1620 psi	11.1 MPa	ASTM D412
Tensile Strength (Break, 73°F (23°C))	3600 psi	24.8 MPa	ASTM D412
Tensile Elongation [2] (Break, 73°F (23°C))	820 %	820 %	ASTM D412
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Durometer Hardness (Shore A, 10 sec)	88	88	ASTM D2240
Fill Analysis	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec^-1	52.4 Pa·s	52.4 Pa·s	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	140 to 194 °F	60 to 90 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.030 %	0.030 %
Rear Temperature	338 to 374 °F	170 to 190 °C
Middle Temperature	374 to 410 °F	190 to 210 °C
Front Temperature	383 to 428 °F	195 to 220 °C
Nozzle Temperature	375 to 428 °F	191 to 220 °C
Mold Temperature	68 to 122 °F	20 to 50 °C
Back Pressure	0.00 to 50.0 psi	0.00 to 0.345 MPa
Screw Speed	50 to 100 rpm	50 to 100 rpm

Notes

[1] Typical values are not to be construed as specifications.

[2] 2 hr

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.