Dynalloy™ FC 3510-60

Thermoplastic Elastomer

Key Characteristics

Product Description			
Dynalloy™ FC 3510-60 is designed for food contact applications that comply with GB 4806.6. Dynalloy™ FC 3510-60 also has excellent bonding on ABS, PC, PC/ABS and Copolyester.			
General			
Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific		
Agency Ratings	• Chinese Standard GB 9685-2016 [1]	• EU 10/2011 [2]	• FDA [3]
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties [4]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04	ASTM D792
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Strength [5, 6] (Yield, 73°F (23°C))	1320 psi	9.10 MPa	ASTM D412
Tensile Elongation [5, 6] (Break, 73°F (23°C))	760 %	760 %	ASTM D412
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Durometer Hardness (Shore A, 10 sec)	60	60	ASTM D2240
Fill Analysis	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec^-1	12.0 Pa·s	12.0 Pa·s	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	122 to 158 °F	50 to 70 °C
Suggested Max Regrind	20 %	20 %
Rear Temperature	302 to 351 °F	150 to 177 °C
Middle Temperature	356 to 437 °F	180 to 225 °C
Front Temperature	374 to 464 °F	190 to 240 °C
Nozzle Temperature	374 to 464 °F	190 to 240 °C
Processing (Melt) Temp	374 to 464 °F	190 to 240 °C
Mold Temperature	60 to 100 °F	16 to 38 °C

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection Notes

Color concentrates with ethylene vinyl acetate (EVA), or low density polyethylene (PE) carriers are most suitable for coloring Dynalloy™ FC 3510-60. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE).

Regrind levels up to 20% can be used with Dynalloy™ FC 3510-60 with minimal property losses, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should be as low as possible. The final determination of regrind effectiveness should be determined by the customer.

The Dynalloy™ FC 3510-60 has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is required.

Notes

[1] Contact AVIENT for a copy of the China GB Compliance letter.

[2] Contact AVIENT for a copy of the EU Compliance letter.

[3] Contact AVIENT for a copy of the FDA Compliance letter.

[4] Typical values are not to be construed as specifications.

[5] Die C

[6] 2 hr

CONTACT INFORMATION

North America

Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America

Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia

Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.