Preliminary ENSOFT SO-300-05A

ENSOFT-S

Product Description : This polyolefin based thermoplastic elastomer (SEBS) compound is produced with food contact compliant raw materials, unfilled, high performance and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery

Additive Packages : T / Heat and UV stabilizer
/

Key Features : Translucent
Excellent ozone, UV and weathering resistance
Rubberlike elasticity in a wide temperature range
Easy colorability with proper MB (PE, PP, etc. based)

Process Method : Injection/multi injection molding

Uses : Industrial applications, personal care, toys, consumer goods, home&kitchen appliances

Revision Date : 01.02.2020

	Value	Unit	Standard
Physical			
Hardness	05	SHORE A	ISO 868 (3 second)
Density	0,9	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	0,2	Mpa	ISO 37, DIN 53504
300% Modulus	0,3	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	2,5	Mpa	ISO 37, DIN 53504,ASTM D412
Elongation at Break	>800	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	7	N/mm	ISO 34-1

Environmental Resistance	
Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good

Data Sheet

Ravago Petrokimya Uretim A.S.
Main Office : *Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey* ***Tel :*** *+90 850 314 70 99*
Plant : *Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey* ***Fax :*** *+90 262 672 10 51*
Mail / Web : *info@ravagopetrokimya.com.tr* *www.ravagopetrokimya.com.tr*

Preliminary ENSOFT SO-300-05A

ENSOFT-S

Detergent	Good
Drying Condition	
Drying Time(hr)	Not required
Drying Temperature(°C)	Not required
Molding Condition (°C)	
1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.

Ravago Petrokimya Uretim A.S.

Main Office : *Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey* ***Tel :*** *+90 850 314 70 99*

Plant : *Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey* ***Fax :*** *+90 262 672 10 51*

Mail / Web : *info@ravagopetrokimya.com.tr* *www.ravagopetrokimya.com.tr*