reSound™ REC AF 7210-170 B

Thermoplastic Elastomer

Key Characteristics

Product Description

reSound REC AF 7210-xx series are easy flowing TPEs designed for a variety of automotive interior applications. They contain a minimum of 37% PCR content and a minimum of 51% total recycling content.

- Excellent surface finish
- Good adhesion to polypropylene
- Excellent performance in static mechanical parts such as seals & grips, panel fasteners, plugs, clips and cable clamps.
- Good UV stability
- reSound REC AF 7210-170 B = black

General			
Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific	• Europe	• North America
Recycled Content	• Yes, 57%		
Features	• Good Processability	• Low Fogging	• Low Odor
Uses	• Automotive Applications • Fasteners	• Gaskets • Overmolding	• Plugs
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	0.990 g/cm³	0.990 g/cm³	ISO 1183
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Strength (Break)	1410 psi	9.70 MPa	ISO 37
Tensile Elongation (Break)	880 %	880 %	ISO 37
Tear Strength	211 lbf/in	37.0 kN/m	ISO 34-1
Compression Set			ISO 815
73°F (23°C), 72 hr	27 %	27 %	
158°F (70°C), 22 hr	48 %	48 %	
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Shore Hardness (Shore A, 10 sec)	70	70	ISO 48-4
Flammability	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Burning Rate	< 3.9 in/min	< 100 mm/min	DIN 75200
Additional Information	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Fogging	< 2.0 mg	< 2.0 mg	DIN 75201
Odor	< 3.00	< 3.00	VDA 270

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	320 to 370 °F	160 to 188 °C
Middle Temperature	350 to 380 °F	177 to 193 °C
Front Temperature	370 to 410 °F	188 to 210 °C
Nozzle Temperature	370 to 420 °F	188 to 216 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Fast	Fast
Back Pressure	0.00 to 120 psi	0.00 to 0.827 MPa
Screw Speed	40 to 100 rpm	40 to 100 rpm

Notes

[1] Typical values are not to be construed as specifications.

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.