ENSOFT SD-654-70A-D

ENSOFT-S

Product Description : This polyolefin based thermoplastic elastomer (SEBS) compound is medium mineral filled, completely recyclable and specifically designed for extrudability at low temperatures. ENSOFT® series can be processed with conventional thermoplastics machinery

Additive Packages : D / Heat and UV stabilizer and lubricant
/

Key Features :
Ozone, UV and weathering resistance
Extra smooth, silky surface appearance
Rubberlike elasticity in a wide temperature range
Ease of processing at lower temperatures
Easy colorability with proper MB (PE, PP, etc. Based)

Process Method : Extrusion, coextrusion, sheet extrusion

Uses : Extruded parts(seals, tubes, profiles, hoses, etc.) for automotive, construction, home appliances, furniture.

Revision Date : 01.03.2018

Data Sheet

	Value	Unit	Standard
Physical			
Hardness	70	SHORE A	ISO 868 (3 second)
Density	1,13	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	1,7	Mpa	ISO 37, DIN 53504
300% Modulus	2,6	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	8,5	Mpa	ISO 37, DIN 53504
Elongation at Break	820	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	38	kN/m	ISO 34-1
Aging			
Compression Set (72h/23°C)	21	%	ISO 815
Compression Set (22h/70°C)	68	%	ISO 815
Thermal			
Max. Dynamic Service Temperature	90	°C	*
Max. Static Service Temperature	135	°C	*

Ravago Petrokimya Üretim A.S
Main Office : *Merkez Mh. Akar Cad. I - Tower No : 3 Kat : 28-29 Şişli - İstanbul Turkey* ***Tel :*** *+90 262 672 10 50*
Plant : *Akse Mh. Fevzi Çakmak Cad. No : 130 Çayırova - Kocaeli 41420 Turkey* ***Fax :*** *+90 262 672 10 51*

ENPLAST Americas, Inc.
Plant : *616 111th Street, Arlington Texas 76011 - USA* ***Tel :*** *+1 817 635 47 70*

Mail : *info@ravagopetrokimya.com.tr*

www.ravagopetrokimya.com.tr

ENSOFT SD-654-70A-D

ENSOFT-S

Environmental Resistance	
Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good
Drying Condition	
Drying Time(hr)	Not required
Drying Temperature(C)	Not required
Extrusion Condition (°C)	
Feed Zone Temperature (°C)	150 - 170
Compression Zone Temperature (°C)	160 - 175
Melting Zone Temperature (°C)	170 - 180
Extruder Head Temperature (°C)	180 - 190
Die Temperature (°C)	180 - 200

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.

Ravago Petrokimya Üretim A.S

Main Office : *Merkez Mh. Akar Cad. I - Tower No : 3 Kat : 28-29 Şişli - İstanbul Turkey* ***Tel :*** *+90 262 672 10 50*

Plant : *Akse Mh. Fevzi Çakmak Cad. No : 130 Çayırova - Kocaeli 41420 Turkey* ***Fax :*** *+90 262 672 10 51*

ENPLAST Americas, Inc.

Plant : *616 111th Street, Arlington Texas 76011 - USA* ***Tel :*** *+1 817 635 47 70*

Mail : *info@ravagopetrokimya.com.tr*

www.ravagopetrokimya.com.tr