Sconablend® TPE 60 X 113 Black

Characteristics **thermoplastic elastomer**

Sconablend® TPE 60 X 113 is a compound for thermoplastic processing with rubber - like properties.
Sconablend® TPE 60 X 113provides a number of outstanding physical properties:

- **high elasticity, flexural and tensile strength**
- **good flexibility at low temperatures and ageing properties**
- **low density**
- **excellent UV resistance (no change of physical properties after 2000h Xenon test)**
- **reuse of in-plant waste without difficulties**
- **excellent processing properties**

Properties / Application

With its wide range of excellent properties and easy colouring, **Sconablend® TPE 60 X 113** can be used for numerous outdoor applications e.g. technical goods for the automotive-, electronic- and cable industry.
Sconablend® TPE 60 X 113 has excellent adhesion to polyolefines, blends and composites based on polyolefines. Therefore it opens interesting possibilities for solutions in the production and processing of hard - soft connections by two component injection-moulding or coextrusion welding, e.g. encapsulation of tools and impellers.

Processing

Sconablend® TPE 60 X 113 can be processed by injection-moulding and extrusion.
Injection-moulding melt temperatures ranging from **180°C to 250°C** and mould temperatures ranging from **30°C to 50°C** are recommended.
The injection rate should be as high as possible.

The extrusion of **Sconablend® TPE 60 X 113** requires melt temperatures between **150°C and 180°C.**

Sconablend® TPE 60 X 113 is not hygroscopic and therefore drying is not necessary if the material is stored properly.

Supply and storage

Sconablend® TPE 60 X 113 is supplied in the form of cylindrical granules in **black tone**. It is delivered in PE bags of 25 kg.

The material should be stored in the original packing in dry rooms at temperatures lower than 35°C and protected from detrimental factors such as water and / or intensive solar radiation.

Ravago Plastics Deutschland GmbH
D- 48565 Steinfurt
Phone : 0049 (0) 2552 9373-0
Fax : 0049 (0) 2552 62380

Sconablend® TPE 60 X 113 Black

Typical characteristics

Eigenschaften/ Caracteristiques/ Characteristics	**Einheit/ Unites/ Units**	**Norm/ Methodes d' essai/ Test method**	**Wert/ Valeurs/ Values**
Dichte/*Dendité/Density*	g/cm³	ISO 1183	1,10 ± 0,03
Härte/*Dureté/Hardness*	Shore A	ISO 868	63 ± 5
Modul, 100%/*Module, 100%/Modulus at 100%*	N/mm²	ISO 527	
- längs/*longitudinal/longitudinal*			> 1,9
- quer/*transversal/transverse*			> 1,2
Zugfestigkeit/*Résistance en traction au seuil/ Tensile strength at yield*	N/mm²	ISO 527	
- längs/*longitudinal/longitudinal*			> 5,8
- quer/*transversal/transverse*			> 9,3
Bruchdehnung/*Allongement de rupture/ Strain at break*	%	ISO 527	
- längs/*longitudinal/longitudinal*			> 630
- quer/*transversal/transverse*			> 850
Druckverformungsrest (22h, 70°C)/*Déformation rémanente/Compression set*	%	ISO 815	< 35

The information, properties and recommendations in this file are based on the current technical knowledge and past experience. They are provided for general guidance only. All recommendations and suggestions are therefore made without guarantee.

Sconablend® - Registered Trademark of **N.V. RAVAGO Plastics S.A.**

Ravago Plastics Deutschland GmbH
D- 48565 Steinfurt
Phone : 0049 (0) 2552 9373-0
Fax : 0049 (0) 2552 62380