TECATEC PEI GW50 PL V01 natural - Composite Materials

Chemical Designation
PEI (Polyetherimide)

Colour
natural

Density
1.9 g/cm^3

Fillers
glass fibres

Main features
- electrically insulating
- inherent flame resistance
- very good mechanical strength

Target Industries
- automotive industry
- mechanical engineering
- oil and gas industry
- safety engineering
- sporting goods

The material is in the phase of further development. The characteristic values of this product may change.

General material information	condition	value	unit	test method	comment
Fibre type		E glass		-	
Fibre architecture		US 7781		-	
Fibre areal weight		296	g/m²	-	
Fibre volume content		50	%	-	
Resin weight content		33.7	%	-	
Areal weight finished product		446	g/m²	-	
Material widths		625x525	mm	others on request	
thickness		1-95	mm	-	
Fibre orientation		0-90°		others on request	

Mechanical properties	condition	value	unit	test method	comment
Tensile strength		450	MPa	ISO 527-4	
Modulus of elasticity (tensile test)		24000	MPa	ISO 527-4	
Flexural strength		570	MPa	ISO 14125	
Modulus of elasticity (flexural test)		26000	MPa	ISO 14125	
Compression strength		670	MPa	ISO 14126	
Compression modulus		27000	MPa	ISO 14126	

Thermal properties	condition	value	unit	test method	comment
Glass transition temperature		217	°C	-	(1) approximate value
Service temperature	long term	180	°C	-	
Service temperature	short term	200	°C	-	
Thermal expansion (CLTE)	in 0° and 90° direction	10	10^{-6} K^{-1}	- 1)	

Predrying	condition	value	unit	test method	comment
Drying temperature		150	°C	-	
Drying time		4-6	h	-	

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. We are neither liable for any values nor content of this datasheet. This exclusion of liability does not apply to claims for damages based on intent, gross negligence or culpable breach of material contractual obligations (cardinal obligations), nor in the case of injury to life, body or health and in the case of product liability as provided by law. Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent. Data sheet parameters are subject to regular review, the current versions can be found at www.ensingerplastics.com

Ensinger Inc. Headquarters 365 Meadowlands Boulevard Washington, PA 15301, USA
Phone 800-243-3221 Sales Phone 800-869-4029
Technical Fax 724-746-9209
sales@ensingerusa.com
Date: 2022/02/14
Version: AD