reSound™ R VX2800-0001 I 65A Black

Thermoplastic Elastomer

Key Characteristics

Product Description	
reSound™ R VX2800-0001 I 65A Black is a general purpose, unfilled TPE compound made with post industrial recycled content that overmolds onto PP.	
General	
Material Status	• Commercial: Active
Regional Availability	• North America
Recycled Content	• Post-Industrial (PIR)/Pre-Consumer, 25%
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.890	0.890	ASTM D792
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Strength [2, 3] (Yield, 73°F (23°C))	650 psi	4.48 MPa	ASTM D412
Tensile Elongation [2, 3] (Break, 73°F (23°C))	600 %	600 %	ASTM D412
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Durometer Hardness (Shore A, 10 sec)	65	65	ASTM D2240
Fill Analysis	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec^-1	6.40 Pa·s	6.40 Pa·s	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	330 to 370 °F	166 to 188 °C
Middle Temperature	350 to 380 °F	177 to 193 °C
Front Temperature	370 to 440 °F	188 to 227 °C
Nozzle Temperature	360 to 420 °F	182 to 216 °C
Processing (Melt) Temp	380 to 440 °F	193 to 227 °C
Mold Temperature	60 to 100 °F	16 to 38 °C

Injection Notes

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).
Regrind levels up to 20% can be used with reSound™ R VX2800-0001 I 65A Black with minimal property losses, provided that the regrind is free of contamination. To
minimize losses during molding, the melt temperature should be as low as possible. The final determination of regrind effectiveness should be
determined by the customer.
Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel
should be emptied if it is idle for periods of 8 - 10 minutes or longer.
Drying is not Required

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Notes

[1] Typical values are not to be construed as specifications.

[2] Die C

[3] 2 hr

CONTACT INFORMATION

North America

Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America

Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia

Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.