Sunday, September 20, 2026

MHCompounds Wire & Cable
TPE 5490

Units English

M. Holland Company -
Thermoplastic Elastomer

Action **Legend (Open)**

General Information

Product Description

TPE 5490 is a natural, olefin-based thermoplastic elastomer (TPE) intended for wire and cable insulation and jacketing. It is designed to offer excellent low temperature flexibility and deformation resistance. TPE 5490 offers good extrusion processing characteristics on either conventional polyethylene or PVC extrusion lines.

TPE 5490 is readily pigmented to a variety of colors using standard wire and cable color concentrates designed for thermoplastic or crosslinked polyolefins. UV weather resistance is obtainable by the addition of a suitable carbon black or UV additive.

Application
TPE 5490 is intended for pump cable, flexible cord insulation, and fixture applications. It is also suitable for use in 75°C wet locations.

General			
Material Status	• Commercial: Active		
Availability	• North America		
Features	• Low Temperature Flexibility		
Uses	• Cable Jacketing	• Insulation	• Wire & Cable Applications
Agency Ratings	• UL 62, Class 36		
Appearance	• Natural Color		
Processing Method	• Extrusion		

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.892		ASTM D792
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength (0.0300 in)	3700	psi	ASTM D412
Tensile Elongation (Break, 0.0300 in)	650	%	ASTM D412
Hardness	**Nominal Value**	**Unit**	**Test Method**
Durometer Hardness			ASTM D2240
Shore A, 0.0300 in	88		
Shore A, 15 sec, 0.0300 in	85		
Shore D, 0.0300 in	34		
Thermal	**Nominal Value**	**Unit**	**Test Method**
Brittleness Temperature	< -50.0	°F	ASTM D746
Heat Deformation (302°F, 30.0 mil)	< 30	%	UL 1581
Aging	**Nominal Value**	**Unit**	**Test Method**
Retention of Tensile Elongation - 7 days at 136°C (30.0 mil)	> 85	%	UL 1581
Retention of Tensile Strength - 7 days at 136°C (30.0 mil)	> 85	%	UL 1581
Electrical	**Nominal Value**	**Unit**	**Test Method**
Dielectric Strength (0.0750 in)	660	V/mil	ASTM D149
Dielectric Constant (0.0750 in, 60 Hz)	2.20		ASTM D150

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	370	°F
Cylinder Zone 2 Temp.	390	°F
Cylinder Zone 3 Temp.	400	°F
Cylinder Zone 4 Temp.	410	°F
Melt Temperature	410	°F
Die Temperature	410 to 450	°F

Notes

[1] Typical properties: these are not to be construed as specifications.

Northbrook, IL 60062
800.872.7370
In Illinois: 847.272.7370
Customer Service FAX: 847.272.7713

UL and the UL logo are trademarks of UL LLC ©, 2026. All Rights Reserved. UL PROSPECTOR

The information presented on this datasheet was acquired by UL IDES from the producer of the material. UL IDES makes substantial efforts to assure the accuracy of this data. However, UL IDES assumes no responsibility for the data values and strongly encourages that upon final material selection, data points are validated with the material supplier.