Dynaflex™ D3202-1000-03 YL

Thermoplastic Elastomer

Key Characteristics

Product Description

Dynaflex D3202-1000-03 YL is an easy processing TPE designed for general purpose applications and is suitable for injection molding, extrusion, blow molding, and thermoforming processes.

- Dry Feel
- Easy Processing
- Good Melt Strength
- Soft Touch

General			
Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific		
Features	• Good Melt Strength	• Good Processability	
Uses	• Consumer Applications	• General Purpose	• Toys
Agency Ratings	• FDA		
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties [1]

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.990	0.990	ASTM D792
Molding Shrinkage - Flow	1.0E-3 to 4.0E-3 in/in	0.10 to 0.40 %	ASTM D955
Elastomers	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Tensile Stress (300% Strain)	933 psi	6.43 MPa	ASTM D412
Tensile Strength [2, 3] (Break, 73°F (23°C))	936 psi	6.45 MPa	ASTM D412
Tensile Elongation [2, 3] (Break, 73°F (23°C))	350 %	350 %	ASTM D412
Tear Strength	176 lbf/in	30.8 kN/m	ASTM D624
Hardness	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Durometer Hardness (Shore A, 10 sec)	58	58	ASTM D2240
Fill Analysis	**Typical Value (English)**	**Typical Value (SI)**	**Test Method**
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec^-1	18.4 Pa·s	18.4 Pa·s	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Rear Temperature	240 to 340 °F	116 to 171 °C
Middle Temperature	330 to 370 °F	166 to 188 °C
Front Temperature	350 to 400 °F	177 to 204 °C
Nozzle Temperature	350 to 400 °F	177 to 204 °C
Mold Temperature	70 to 90 °F	21 to 32 °C
Back Pressure	0.00 to 110 psi	0.00 to 0.758 MPa
Screw Speed	40 to 100 rpm	40 to 100 rpm

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection Notes

Color concentrates with ethylene vinyl acetate (EVA) carriers are most suitable for coloring Dynaflex D3202-1000-03 YL. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow rate of 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. A high color match consistency may be obtained by using precolored compounds available from GLS. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polystyrene (PS) or polypropylene (PP).

Dynaflex D3202-1000-03 YL has good melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 5 - 8 minutes or longer.

Drying is not Required

Injection Speed: 1 to 3 in/sec
1st Stage - Boost Pressure: 200 to 800 psi
2nd Stage - Hold Pressure: 30% of Boost
Hold Time (Thick Part): 3 to 10 sec
Hold Time (Thin Part): 1 to 3 sec

Notes

[1] Typical values are not to be construed as specifications.

[2] Die C

[3] 2 hr

CONTACT INFORMATION

North America
Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States , 44012
+1 440 930 1000
+1 844 4AVIENT

South America
Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia
Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe
Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35

avient.com

Copyright ©, 2026 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.