Product information

Brand Name
THERMOLAST® K

Product Code
HTC1500/117

The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision from time to time as new knowledge and data becomes known to us. All stated values are typical values observed by us based on limited sample test results and are not a product specification. The responsibility to conduct testing to determine (i) suitability of use for a particular process or end-use applications, (ii) associated interactions with other product components, and (iii) any resulting safety risks remains with the customer and end user.

Please note that, as compound manufacturer, we are generally not aware of the subsequent area of application and the associated interactions with other product components, as well as any resulting safety risks, unless you discuss this with us in advance. For this reason, the use of this compound in safety-relevant applications is not permitted without our prior written consent.

Thermally conductive TPE applications with adhesion to PA

Processing Method
Injection Molding

Color / RAL DESIGN
natural

Typical applications
- Seals
- Over molded housing
- Components for cooling circuits
- Applications for new mobility
- Components for charging systems
- Battery technology applications
- LED

Material advantages
- Thermal conductivity
- Adhesion to PA6 and PA6.6, up to 50% glass fiber
- Colorable
- Dry haptics
- Temperature stability up to 90 °C

The shelf life of the TPE granules is 24 months from delivery if storage instructions are observed and the product is stored in the unopened original KRAIBURG TPE packaging. Store in dry conditions at room temperature (below 40 °C) away from heat sources and direct sunlight! Contact with nitrogen oxides must be avoided during storage!

KRAIBURG TPE
CUSTOM-ENGINEERED TPE AND MORE

Datasheet

Brand Name
THERMOLAST® K

Product Code
HTC1500/117

Product properties	Value	Unit	Standard
Hardness	59	Shore A	DIN ISO 48-4
Density	1.393	g/cm3	DIN EN ISO 1183-1
Tensile Strength[1]	2.5	MPa	DIN 53504/ISO 37
Elongation at Break[1]	122	%	DIN 53504/ISO 37
Tear Resistance	13.9	N/mm	DIN ISO 34-1 Method B (b) (Graves)
Thermal Conductivity (X)	3.0	W/m*K	ISO 18755 (laser flash method)
Thermal Conductivity (Y)	3.0	W/m*K	ISO 18755 (laser flash method)
Thermal Conductivity (Z)	1.5	W/m*K	ISO 18755 (laser flash method)
CS 72 h/23 °C	22	%	DIN ISO 815-1 Method A
CS 24 h/100 °C	86	%	DIN ISO 815-1 Method A
CS 24 h/70 °C	51	%	DIN ISO 815-1 Method A
Flow Spiral [760 bar, 200 °C]	29.0	cm	DSOP Lab 2032

[1]Deviating from ISO 37 standard test piece S2 is tested with a traverse speed of 200 mm/min.
All values published in this data sheet are rounded average values.

The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision from time to time as new knowledge and data becomes known to us. All stated values are typical values observed by us based on limited sample test results and are not a product specification. The responsibility to conduct testing to determine (i) suitability of use for a particular process or end-use applications, (ii) associated interactions with other product components, and (iii) any resulting safety risks remains with the customer and end user.

Please note that, as compound manufacturer, we are generally not aware of the subsequent area of application and the associated interactions with other product components, as well as any resulting safety risks, unless you discuss this with us in advance. For this reason, the use of this compound in safety-relevant applications is not permitted without our prior written consent.

The shelf life of the TPE granules is 24 months from delivery if storage instructions are observed and the product is stored in the unopened original KRAIBURG TPE packaging. Store in dry conditions at room temperature (below 40 °C) away from heat sources and direct sunlight! Contact with nitrogen oxides must be avoided during storage!

For further information and individual custom solutions please contact our customer service.

WALDKRAIBURG - GERMANY
KRAIBURG TPE GMBH & CO. KG
info@kraiburg-tpe.com
+49 8638 9810-0

SELANGOR / KUALA LUMPUR - MALAYSIA
KRAIBURG TPE TECHNOLOGY (M) SDN.BHD.
info-asia@kraiburg-tpe.com
+60 3 9545 6393

BUFORD, GA - UNITED STATES
KRAIBURG TPE CORPORATION
info-america@kraiburg-tpe.com
+1 678 584-5020

WhatsApp Support
+49 172 8533045